

# STTC

绍兴纺织品检测中心  
SHAOXING TEXTILE TESTING CENTER



## 检测报告 TEST REPORT

No.: W070861  
Receipt Date: 08/17/2007  
Performance Date: 08/21/2007

Page 1 of 1

Applicant : SHAOXING COUNTY MAOXIN KNITTING CO., LTD  
Commodity : TABLE CLOTH  
Quantity/Colour : ONE PIECE/BLACK  
Resource of sample : SENT BY THE APPLICANT

TEST ITEMS : BURNING BEHAVIOUR

TEST METHODS: GB/T5455-1997 《Textiles-Burning behaviour-Vertical method》

TEST RESULTS :

WALEWISE  
AFTERFLAME TIME: 0S  
AFTERGLOW TIME: 0S  
DAMAGED LENGTH: 107MM  
MELTING ; NO DRIPPING


CAOSSWISE  
AFTERFLAME TIME: 0S  
AFTERGLOW TIME: 0S  
DAMAGED LENGTH: 91MM  
MELTING ; NO DRIPPING  
(TESTING CONDITION : T 26°C RH 60% GAS: BUTANE GAS)

ATTACHED SAMPLE:



黑色

Remarks: 1. The report is responsible for the sample above mentioned.  
2. The report shall not be reproduced without written approval of the centre.  
3. In case of divergence, the chinese text shall be regarded as authentic.



Signer:

This report is only for the use of the client to realize the quality of the sample. The test results mentioned here with values are only for the sample's batch unless otherwise stated. Without the written permission of the center, the report may not be reprinted, reproduced or distributed in any form or by any means, electronic or mechanical, including photocopying, recording, or by any information storage and retrieval system. The issuance of this report does not constitute a warranty or a claim of liability for the client. All rights reserved. Address: No.301 East Yanan Road, Shaoxing City, Zhejiang Province, China  
Tel: 86-575-88125328 Fax: 86-575-88651932  
http: www.sttc.com.cn  
email: sttc@sttc.zj.gov.cn

0000186