

# STTC

绍兴纺织品检测中心  
SHAOXING TEXTILE TESTING CENTER



## 检测报告 TEST REPORT

No.:W100267  
Receipt Date:07/21/2010  
Performance Date:07/28/2010

Page 1 of 1

Applicant :SHAOXING COUNTY MAOXIN KNITTING CO.,LTD  
Commodity : TABLE CLOTH  
Quantity/Colour :ONE PIECE/WHITE  
Resource of sample :SENT BY THE APPLICANT

TEST ITEMS : BURNING BEHAVIOUR

TEST METHODS: GB/T5455-1997 《Textiles-Burning behaviour-Vertical method》

TEST RESULTS :

WALEWISE

AFTERFLAME TIME: 0S  
AFTERGLOW TIME:0S  
DAMAGED LENGTH:107MM  
MELTING ; NO DRIPPING

CAOSSWISE


AFTERFLAME TIME:0S  
AFTERGLOW TIME:0S  
DAMAGED LENGTH:91MM  
MELTING ; NO DRIPPING  
(TESTING CONDITION :T 26°C RH 60%; GAS: BUTANE GAS)

ATTACHED SAMPLE:



Remarks:1.The report is responsible for the sample above mentioned.  
2.The report shall not be reproduced or distributed without written approval of the centre.  
3.In case of divergence, the chinese text shall be regarded as authentic.

The end



Signer:



This report is only for the use of the client to realize the quality of the sample. The test results mentioned here with relate only to the sample(s) tested unless otherwise stated. Without the written permission of the center, the report may not be reproduced except in full. The issuance of this report does not exonerate buyers or sellers from exercising all their rights and discharging all their liabilities under the Contract of Sale stipulations to the contrary are not binding on the Center.

add No.30 East Yan'an Road, Shaoxing City,Zhejiang Province,China,312000  
tel 86-575-88125328 fax 86-575-88651732  
http www.sttc.com.cn  
email sttc@sx.zj.gov.cn

0000186